

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61L 15/00, C08K 5/00 // C08L 101:00		A1	(11) International Publication Number: WO 99/64077 (43) International Publication Date: 16 December 1999 (16.12.99)
(21) International Application Number: PCT/IB99/00997 (22) International Filing Date: 1 June 1999 (01.06.99) (30) Priority Data: 98110597.6 9 June 1998 (09.06.98) EP (71) Applicant (for all designated States except US): THE PROCTER & GAMBLE COMPANY [US/US]; One Procter Gamble Plaza, Cincinnati, OH 45202 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): CORZANI, Italo [IT/IT]; Via Fontevicchia, 40, I-66100 Chieti (IT). PALUMBO, Gianfranco [IT/DE]; Georgenfeld 7, D-61348 Bad Homburg (DE). (74) Agents: REED, T., David et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217-1087 (US).			(81) Designated States: AE, AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: LOW VISCOSITY THERMOPLASTIC COMPOSITIONS FOR MOISTURE VAPOUR PERMEABLE STRUCTURES AND THE UTILISATION THEREOF IN ABSORBENT ARTICLES			
(57) Abstract <p>The present invention relates to thermoplastic compositions for making a liquid impermeable moisture vapour permeable layer by coating the composition onto a substrate. The thermoplastic compositions comprise preferred thermoplastic polymers and suitable plasticisers to adjust the viscosity of the composition at the process conditions. The layers made from the thermoplastic compositions of the present invention can find a variety of applications wherein moisture vapour permeability is desirable, such as within absorbent articles for example diapers, sanitary napkins, panty liners and incontinence products, and also protective bedding covers, protective clothing and the like.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**LOW VISCOSITY THERMOPLASTIC COMPOSITIONS FOR MOISTURE
VAPOUR PERMEABLE STRUCTURES AND THE UTILISATION THEREOF IN
ABSORBENT ARTICLES**

Field of the Invention

The present invention relates to thermoplastic compositions for making a moisture vapour permeable, liquid impermeable layer by coating the composition onto a substrate. The compositions of the present invention can find a variety of applications, wherein moisture vapour permeability is desirable for example within absorbent articles such as diapers, sanitary napkins, panty liners and incontinence products, protective bedding covers, protective clothing and the like.

Background of the Invention

Thermoplastic films which provide a liquid barrier in addition to providing moisture vapour permeability are known in the art. Particularly preferred are hydrophilic continuous films that do not allow the flow of moisture vapour through open pores or apertures in the material, but do transfer substantial amounts of moisture vapour through the film by absorbing water on one side of the film where the moisture vapour concentration is higher, and desorbing or evaporating it on the opposite side of the film where the moisture vapour concentration is lower.

For example WO 95/16746 discloses films prepared from mixtures of a) block copolyether ester, block copolyether amides (e.g. Pebax™) and or polyurethane and b) thermoplastic polymer which is incompatible with a, and c)

a compatibiliser. The films are liquid impermeable and have moisture vapour permeability of about $700 \text{ g/m}^2\text{-day}$. Also, US 5,447,783 discloses a vapour permeable water resistant multi component film structure having at least three layers. The outer layers are hydrophobic copolyetherester elastomers having a thickness of 1.3-7.6 micrometers and a WVTR of $400\text{-}2500 \text{ g/m}^2\text{-}24\text{h}$ and the inner layer is a hydrophilic copolyetherester elastomer having a thickness of 7.6-152 micrometers and a WVTR of at least $3500 \text{ g/m}^2\text{-}24\text{h}$.

US 5,445,875 discloses a waterproof, bloodproof and virusproof breathable laminate. The laminate comprises a woven/nonwoven fabric and an extruded film such as Hytrel™ having a thickness of about 1mil (25.4 micrometers).

Other composite laminates are described for example in US 5,599,610 which discloses tri-laminated fabric for surgical gowns comprising outer layers of woven fabric and an inner layer of a microporous polyurethane membrane. The microporous film has a thickness of 12-55 micrometers and a MVTR of $1100 \text{ g/m}^2\text{-}24\text{h}$ upright and $5500 \text{ g/m}^2\text{-}24\text{h}$ inverted (ASTM E96-B). Polyether-polyurethane adhesive is used to join the layers.

Similarly, US 5,532,053 discloses a high moisture transmission medical film which can be laminated onto a nonwoven material. The laminate film comprises a first layer of polyetherester copolymer and second and third layers selected from a specified group of polymers. The film has a MVTR of greater than $750 \text{ g/m}^2\text{-}24\text{h}$ (ASTM F1249) and a thickness of less than 1mil (25.4micrometer) preferably 0.6 mil to 0.75 mil (15 -19 micrometers).

US 4,938,752 discloses absorbent articles comprising films of copolyether esters which have reduced water permeability, a water vapour permeability of $500 \text{ g/m}^2\text{-}24\text{h}$ (as measured in a specified described test) and a thickness of 5-35 micrometers. There is no disclosure of a supportive substrate.

US 4,493,870 discloses a flexible layered waterproof product comprising a textile material covered with a film of a copolyetherester having an MVTR of at least $1000 \text{ g/m}^2\text{-}24\text{h}$ (ASTM E96- 66) having a thickness of 5 to 35 micrometers.

GB 2024100 discloses a flexible layered water resistant article comprising a microporous hydrophobic outer layer which is moisture vapour permeable but resist liquids and a hydrophilic inner layer of polyetherpolyurethane having a MVTR of above 1000 g/m²·24h.

Compositions known for providing hydrophilic continuous moisture vapour permeable, liquid impermeable films or layers include thermoplastic polymers such as polyurethanes, poly-ether-amides block copolymers, polyethylene-acrylic acid copolymers, polyethylene oxide and its copolymers, poly lactide and copolymers, polyamides, polyester block copolymers, sulfonated polyesters, poly-ether-ester block copolymers, poly-ether-ester-amide block copolymers, polyacrylates, polyacrylic acids and derivatives, ionomers, polyethylene-vinyl acetate with a vinyl acetate content of more than 28% by weight, polyvinyl alcohol and its copolymers, polyvinyl ethers and their copolymers, poly-2-ethyl-oxazoline and derivatives, polyvinyl pyrrolidone and its copolymers, thermoplastic cellulose derivatives, or mixtures thereof. Such compositions can be used for making layers and films featuring high values of moisture vapour permeability while being liquid impermeable, which therefore are particularly preferred for incorporation in disposable absorbent articles.

However, a problem associated with films and layers made from the above mentioned thermoplastic compositions is that such compositions are typically highly viscous in the plastic state at the process conditions, and are processable only by means of extrusion techniques. Extrusion processes for making films and layers from thermoplastic polymers are well known, but have the disadvantage of being rather complex; they in fact require expensive equipment, typically comprising a high power screw extruder to force the material in the plastic state through a slit die to form the film or layer. Extrusion process conditions also typically involve rather high temperatures and pressures. Moreover an extrusion apparatus for the formation of a film or layer cannot be easily incorporated into a production line, e.g. of disposable absorbent products. Extrusion processes moreover are not suitable for the production of films having a particularly low thickness, e.g. in the range of 5-10 µm.

Furthermore, in case of laminated composite structures, in which i.e. a layer of the preferred moisture vapour permeable, liquid impermeable

composition is laminated to a substrate, e.g. a fibrous layer, the addition of an adhesive in order to ensure permanent fixation of the film onto the substrate is often required. However, this in turn detrimentally affects the overall moisture vapour permeability of the resulting composite, and adds complexity to the production process.

Hence, there is a need to provide compositions for making a hydrophilic continuous moisture vapour permeable, liquid impermeable layer having preferred characteristics of moisture vapour permeability and liquid imperviousness which are also readily processable so as to provide a preferably thin film coating onto a substrate, so avoiding the need of complex traditional extrusion apparatuses.

Summary of the Invention

The present invention relates to a thermoplastic composition comprising:

a thermoplastic polymer or mixture of polymers having a viscosity higher than 5000 poise at a temperature of 20°C above the DSC melting point of the polymer or mixture of polymers, evaluated as described in the text, and at a frequency of 1 rad/sec, the thermoplastic polymers being selected from the group consisting of polyurethanes, poly-ether-amides block copolymers, polyethylene-acrylic acid copolymers, polyethylene oxide and its copolymers, poly lactide and copolymers, polyamides, polyester block copolymers, sulfonated polyesters, poly-ether-ester block copolymers, poly-ether-ester-amide block copolymers, polyacrylates, polyacrylic acids and derivatives, ionomers, polyethylene-vinyl acetate with a vinyl acetate content of more than 28% by weight, polyvinyl alcohol and its copolymers, polyvinyl ethers and their copolymers, poly-2-ethyl-oxazoline and derivatives, polyvinyl pyrrolidone and its copolymers, thermoplastic cellulose derivatives, or mixtures thereof,

a suitable compatible plasticiser or blend of plasticisers for adjusting said viscosity,

wherein said thermoplastic composition has a viscosity of from 50 poise to 4000 poise at a frequency of 1 rad/s at a temperature of 210°C or less and a viscosity of less than 2000 poise at a frequency of 1000 rad/s at a temperature of 210°C or less.

Detailed Description of the Invention

Preferred thermoplastic polymers for providing hydrophilic continuous moisture vapour permeable, liquid impermeable films or layers are polyurethanes, poly-ether-amides block copolymers, polyethylene-acrylic acid copolymers, polyethylene oxide and its copolymers, poly lactide and copolymers, polyamides, polyester block copolymers, sulfonated polyesters, poly-ether-ester block copolymers, poly-ether-ester-amide block copolymers, polyacrylates, polyacrylic acids and derivatives, ionomers, polyethylene-vinyl acetate with a vinyl acetate content of more than 28% by weight, polyvinyl alcohol and its copolymers, polyvinyl ethers and their copolymers, poly-2-ethyl-oxazoline and derivatives, polyvinyl pyrrolidone and its copolymers, thermoplastic cellulose derivatives, and mixtures thereof. Among the above mentioned thermoplastic polymers particularly preferred are thermoplastic poly-ether-amide block copolymers (e.g. Pebax™), thermoplastic poly-ether-ester-amide block copolymers, thermoplastic polyester block copolymers (e.g. Hytrel™), thermoplastic polyurethanes (e.g. Estane™), or mixtures thereof. Such thermoplastic polymers or mixture of polymers are typically highly viscous in the melted state at the process conditions that are typical of the known processes of film or layer formation, e.g. an extrusion process involving a high power screw extruder. Specifically the thermoplastic polymer or mixture of polymers typically have a viscosity higher than 5000 poise at a temperature of 20°C above the DSC (Differential Scanning Calorimetry) melting point, which is the temperature identified as that corresponding to the DSC peak, or corresponding to the highest DSC peak in case of a mixture of polymers showing more than one peak, and at a frequency of 1 rad/sec.

The viscosity of the thermoplastic compositions of the present invention is adjusted by providing the thermoplastic composition comprising the thermoplastic polymer or mixture of polymers with a suitable plasticiser, or

blend of plasticisers, that is compatible with the thermoplastic polymers and that lowers the viscosity of the thermoplastic composition in the melted state.

According to the present invention the thermoplastic compositions have the following complex viscosities (η^*):

50 poise $< \eta^* < 4000$ poise, preferably 100 poise $< \eta^* < 2000$ poise, more preferably 100 poise $< \eta^* < 1000$ poise, at a frequency of 1 rad/s at a temperature of 210°C or less and $\eta^* < 2000$ poise, preferably $\eta^* < 1000$ poise, more preferably $\eta^* < 500$ poise at a frequency of 1000 rad/s at a process temperature (T) of 210°C or less, wherein η^* represents the complex viscosity of the thermoplastic polymeric composition. Preferably the temperature T is 200°C or less and more preferably 180°C or less and most preferably from 200°C to 50°C.

It has been surprisingly found that thermoplastic compositions having the complex viscosity described allow for a film or layer to be coated onto a substrate using typical coating conditions and apparatuses known in the art for the coating of low viscosities hot melt compositions in a layer having a required thickness onto a substrate, while keeping the advantageous characteristics of the preferred thermoplastic polymers in providing hydrophilic continuous moisture vapour permeable, liquid impermeable layers or films.

It has also been found that thermoplastic compositions having such viscosities can provide very thin films or layers.

Suitable plasticisers for use in the thermoplastic compositions according to the present invention include citric acid esters, tartaric acid esters, glycerol and its esters, adipates, sebacates, sorbitol, epoxidized vegetal oils, polymerised vegetal oils, polyols, phthalates, liquid polyesters, glycolates, p-toluene sulfonamide and derivatives, glycols and polyglycols, sorbitan esters, phosphates, monocarboxylic fatty acids (C_8-C_{22}) and their derivatives, and mixtures thereof.

Preferably the thermoplastic composition of the present invention comprises from 10% to 80%, more preferably from 25% to 70% by weight of the

thermoplastic composition, of the thermoplastic polymer or mixture of polymers, and from 20% to 90%, preferably from 30% to 75% by weight of the thermoplastic composition, of the suitable plasticiser or blend of plasticisers.

The thermoplastic compositions of the present invention may in addition comprise additional optional components to further improve the processability of the compositions and also the mechanical characteristics as well as other characteristics as tackiness, resistance to ageing by light and oxygen, visual appearance etc., of the films or layers formed from such thermoplastic compositions.

Such optional components include tackifying resins or blends of tackifying resins having a softening point of 125°C or less. Preferred resins, which may be present by up to 50% by weight of the thermoplastic composition, may be selected from rosins and rosin esters, hydrocarbon resins, aliphatic resins, terpene and terpene-phenolic resins, aromatic resins, synthetic C₅ resins, mixtures of synthetic C₅-C₉ resins, and mixtures thereof. Other optional components of said thermoplastic compositions include anti-oxidants, anti-ultraviolet, pigments and mixtures thereof, which may be present within the composition at a level of up to 10% by weight of the composition.

A thermoplastic composition according to the present invention can be manufactured with a process that will typically comprise the steps of providing the thermoplastic polymer or mixture of polymers and the suitable plasticiser or blend of plasticisers, heating the components and compounding them, e.g. with a known suitable mixer to form the thermoplastic composition in the molten state having the desired complex viscosity η^* .

According to the present invention a moisture vapour permeable, liquid impervious layer can be formed from the thermoplastic composition of the present invention by coating said thermoplastic composition onto a substrate. The films or layers formed from the thermoplastic compositions of the present invention preferably have a moisture vapour transport rate of at least 100 g/m²·24h, preferably at least 300 g/m²·24h, most preferably at least 500 g/m²·24h, with a thickness of at least 0.5 μ m.

A process for making a layer or film from a thermoplastic composition according to the present invention typically comprises the steps of providing said composition, heating it to make it flowable, and coating said composition in the molten state onto a substrate in a layer having the desired thickness. While said substrate can be simply a formation substrate, onto which the thermoplastic composition is coated in order to form a film or layer of the desired thickness which is subsequently separated from said substrate and used as such, in an embodiment of the present invention a moisture vapour permeable, water impervious composite can also be formed which comprises the thermoplastic composition and a substrate onto which said thermoplastic composition is coated, wherein the substrate is also preferably moisture vapour permeable.

Such embodiment of the present invention provides a moisture vapour permeable, liquid impervious composite wherein the contribution of the layer formed from the thermoplastic composition of the present invention to the performance of the composite material resides only in the provision of a liquid barrier and hence could be advantageously provided as thinly as possible. The remaining performance physical criterion being preferably provided by the provided substrate, that therefore preferably acts also as a support layer.

The substrate, or support layer may be any useful layer which is preferably also moisture vapour permeable, preferably having a moisture vapour permeability of at least $100 \text{ g/m}^2 \cdot 24\text{h}$, more preferably at least $300 \text{ g/m}^2 \cdot 24\text{h}$, and most preferably at least $500 \text{ g/m}^2 \cdot 24\text{h}$.

Suitable substrates for use herein as support layers include two dimensional, planar micro and macro-porous films; macroscopically expanded films; formed apertured films; nonwoven and woven layers. According to the present invention the apertures in said layer may be of any configuration, but are preferably spherical or oblong and may also be of varying dimensions. The apertures preferably are evenly distributed across the entire surface of the layer, however layers having only certain regions of the surface having apertures are also envisioned.

Suitable two dimensional porous planar layers of the backsheet may be made of any material known in the art, but are preferably manufactured from

commonly available polymeric materials. Suitable materials are for example Goretex™ or Sympatex™ type materials well known in the art for their application in so-called breathable clothing. Other suitable materials include XMP-1001 of Minnesota Mining and Manufacturing Company, St. Paul, Minnesota, USA and Exxair XBF-101W, supplied by the Exxon Chemical Company. As used herein the term two dimensional planar layer refers to layers having a depth of less than 1 mm, preferably less than 0.5 mm, wherein the apertures have an average uniform diameter along their length and which do not protrude out of the plane of the layer. The apertured materials for use as a backsheet in the present invention may be produced using any of the methods known in the art such as described in EPO 293 482 and the references therein. In addition the dimensions of the apertures produced by this method may be increased by applying a force across the plane of the backsheet layer (i.e. stretching the layer).

Suitable apertured formed films include films which have discrete apertures which extend beyond the horizontal plane of the garment facing surface of the layer towards the core thereby forming protuberances. The protuberances have an orifice located at its terminating end. Preferably said protuberances are of a funnel shape, similar to those described in US 3,929,135. The apertures located within the plane and the orifices located at the terminating end of protuberance themselves maybe circular or non circular provided the cross sectional dimension or area of the orifice at the termination of the protuberance is smaller than the cross sectional dimension or area of the aperture located within the garment facing surface of the layer. Preferably said apertured performed films are uni directional such that they have at least substantially, if not complete one directional fluid transport towards the core.

Suitable macroscopically expanded films for use herein include films as described in for example in US 4,637,819 and US 4,591,523.

Preferred support layers for use herein include woven and nonwoven layers, most preferably hydrophobic fibrous layers such as hydrophobic nonwoven.

The composites of this preferred embodiment of the present invention are particularly advantageous as they allow the possibility of providing a composite wherein the thermoplastic composition may be coated onto the support substrate as a layer with the desired thickness. Typical coating conditions and apparatuses known in the art for the direct coating of low viscosities hot melts can be readily utilised in order to provide the thermoplastic composition at the desired thickness.

A possible method for forming a composite laminate by coating the thermoplastic composition onto a substrate acting as a support layer is described in PCT application WO 96/25902.

At least at the coating temperature, the thermoplastic composition in form of a layer preferably exhibits adhesive properties on the supportive substrate in order to form the preferred composite such that no additional adhesive is required to achieve a permanent attachment between the thermoplastic composition and the substrate. In some applications it may be also desirable that the thermoplastic composition remains tacky at any temperature i.e. it is formulated so to have the typical characteristics of a pressure sensitive adhesive.

The thermoplastic compositions of the present invention and the moisture vapour permeable, liquid impervious layers and composites formed therefrom find utility in a number of applications wherein liquid imperviousness and moisture vapour permeability are desirable. In particular the present invention can be effectively utilised within absorbent articles such as diapers, sanitary napkins, panty liners and incontinence products; perspiration pads such as underarm-, wrist- and head perspiration pads, collar inserts, shoe inserts, hat bands and breast pads; protective bedding covers, protective clothing and the like. Preferably the moisture vapour permeable, liquid impervious layers and composites formed from the thermoplastic compositions of the present invention have a moisture vapour transfer rate of at least $100 \text{ g/m}^2 \cdot 24\text{h}$, more preferably at least $300 \text{ g/m}^2 \cdot 24\text{h}$, and most preferably at least $500 \text{ g/m}^2 \cdot 24\text{h}$.

A moisture vapour permeable, liquid impervious composite structure formed by coating the thermoplastic composition of the present invention onto a

suitable substrate finds particular utility as the backsheet for absorbent articles especially sanitary napkins and panty liners. Such articles will typically comprise components known to the skilled person such as a liquid pervious topsheet, an absorbent core and backsheet and may optionally comprise fastening means, wings, and the like.

Example:

A polyether-amide block copolymer available from Elf Atochem (France) commercialised under the trade name Pebax MV 1074 was compounded with Triethyl Citrate available from Aldrich Co. and Irganox 1010 (anti oxidant agent) available from Ciba-Geigy.

The polymer has a DSC peak melting point of 158°C and at 178°C and at the frequency of 1 rad/s shows a complex viscosity of 6410 Poise.

The final formulation in percent by weight had the following composition:

30%	Pebax MV 1074
69%	Triethyl Citrate
1%	Irganox 1010

The blend was melt extruded at 160°C to obtain a film having a thickness equal to 5µm. At the extruding temperature it was found to have complex viscosities of 517 poise and 172 Poise respectively at 1 and 1000 rad/s shear rate. The film was then laminated directly onto a substrate constituted by a carded hydrophobic 100% polypropylene nonwoven 34 g/m² (support layer) commercialised under the trade name Sawabond 4326, available from Sandler (Germany). The composite substrate had a moisture vapour transfer rate of 2530 g/m².24hrs.

According to the present invention the complex viscosity is measured using a Rheometer RDA-II available from Rheometrics Co. Water vapour permeability is measured at 23°C according to the ASTM E-96 "Upright Cup" method.

WHAT IS CLAIMED IS:

1. A thermoplastic composition comprising:

a thermoplastic polymer or mixture of polymers having a viscosity higher than 5000 poise at a temperature of 20°C above the DSC melting point of said polymer or mixture of polymers and at a frequency of 1 rad/sec, said thermoplastic polymers selected from the group consisting of polyurethanes, poly-ether-amides block copolymers, polyethylene-acrylic acid copolymers, polyethylene oxide and its copolymers, poly lactide and copolymers, polyamides, polyester block copolymers, sulfonated polyesters, poly-ether-ester block copolymers, poly-ether-ester-amide block copolymers, polyacrylates, polyacrylic acids and derivatives, ionomers, polyethylene-vinyl acetate with a vinyl acetate content of more than 28% by weight, polyvinyl alcohol and its copolymers, polyvinyl ethers and their copolymers, poly-2-ethyl-oxazoline and derivatives, polyvinyl pyrrolidone and its copolymers, thermoplastic cellulose derivatives, or mixtures thereof,

a suitable compatible plasticiser or blend of plasticisers for adjusting said viscosity,

wherein said thermoplastic composition has a viscosity of from 50 poise to 4000 poise at a frequency of 1 rad/s at a temperature of 210°C or less and a viscosity of less than 2000 poise at a frequency of 1000 rad/s at a temperature of 210°C or less.

2. A thermoplastic composition according to claim 1, wherein said thermoplastic polymer comprises thermoplastic poly-ether-amide block copolymers, thermoplastic poly-ether-ester-amide block copolymers, thermoplastic polyester block copolymers, thermoplastic polyurethanes, or mixtures thereof.
3. A thermoplastic composition according to any preceding claim, wherein said composition comprises:

from 10% to 80%, preferably from 25% to 70%, by weight of said thermoplastic composition, of said polymer or mixture of polymers,

from 20% to 90%, preferably from 30 to 75%, by weight of said thermoplastic composition, of said plasticiser or blend of plasticisers,

from 0 to 50% by weight of a suitable compatible tackifier resin.

4. A thermoplastic composition according to any preceding claim, wherein said plasticisers are selected from citric acid esters, tartaric acid esters, glycerol and its esters, adipates, sebacates, sorbitol, epoxidized vegetal oils, polymerised vegetal oils, polyols, phthalates, liquid polyesters, glycolates, p-toluene sulfonamide and derivatives, glycols and polyglycols, sorbitan esters, phosphates, monocarboxylic fatty acids (C₈-C₂₂) and their derivatives, and mixtures thereof.
5. A thermoplastic composition according to any preceding claim, wherein said tackifier resins are selected from rosins and rosin esters, hydrocarbon resins, aliphatic resins, terpene and terpene-phenolic resins, aromatic resins, synthetic C₅ resins, mixtures of synthetic C₅-C₉ resins, and mixtures thereof.
6. A moisture vapour permeable layer formed from the thermoplastic composition of claim 1, wherein said layer is liquid impervious and has a water vapour transmission rate (WVTR) of at least 300 g/m²·24h with a thickness of said layer of at least 0.5 µm.
7. A moisture vapour permeable, liquid impervious composite comprising the layer of claim 6 coated onto a substrate, said substrate being moisture vapour permeable.
8. An absorbent article comprising a moisture vapour permeable, liquid impervious layer or composite according to claims 6 or 7.

9. A process for making a thermoplastic composition according to claim 1, comprising the steps of:
- providing said thermoplastic polymer or mixture of polymers,
 - providing said suitable plasticiser or blend of plasticisers,
 - heating said thermoplastic polymer or mixture of polymers and said plasticiser or blend of plasticisers and compounding them to form said thermoplastic composition in the molten state.
10. A process for making a layer from the thermoplastic composition of claim 1, comprising the steps of:
- providing said thermoplastic composition,
 - heating said thermoplastic composition to make it flowable,
 - coating said thermoplastic composition onto a substrate in a layer having a desired thickness.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 99/00997

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 A61L15/00 C08K5/00 //C08L101:00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 A61L C08L C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 805 182 A (KUREHA CHEMICAL IND CO LTD) 5 November 1997 (1997-11-05) claims 1,7,9 page 5, line 11 - line 15 page 7, line 50 - line 58 table 1	1,3,4,9
X	EP 0 806 283 A (KUREHA CHEMICAL IND CO LTD) 12 November 1997 (1997-11-12) claims 1,9,11 page 6, line 9 - line 13 page 9, line 43 - line 52 table 1	1,3,4,9

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

27 July 1999

Date of mailing of the international search report

05/08/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040. Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Niaounakis, M

INTERNATIONAL SEARCH REPORT

International Application No
PCT/IB 99/00997

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 424 346 A (SINCLAIR RICHARD G) 13 June 1995 (1995-06-13) claims 1,5,15 column 8, line 17 - line 19; figure 5; example 30 column 9, line 58 - line 61 ---	1
A	US 4 123 410 A (LEE JR GIM F) 31 October 1978 (1978-10-31) claims 1,4,9 table 1 -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IB 99/00997

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0805182	A	05-11-1997	JP 10072529 A	17-03-1998
EP 0806283	A	12-11-1997	JP 10337772 A	22-12-1998
US 5424346	A	13-06-1995	AU 8660191 A	30-03-1992
			CA 2091185 A	07-03-1992
			EP 0548284 A	30-06-1993
			FI 930992 A	05-03-1993
			JP 6504799 T	02-06-1994
			WO 9204413 A	19-03-1992
			US 5767222 A	16-06-1998
			US 5444113 A	22-08-1995
			US 5556895 A	17-09-1996
			US 5801223 A	01-09-1998
			US 5760118 A	02-06-1998
			US 5834582 A	10-11-1998
			US 5502158 A	26-03-1996
			AT 177134 T	15-03-1999
			DE 68928938 D	08-04-1999
			DK 50391 A	20-03-1991
			EP 0428620 A	29-05-1991
			HU 64576 A	28-01-1994
			WO 9001521 A	22-02-1990
			AU 634723 B	04-03-1993
			CA 1339026 A	25-03-1997
			JP 2725870 B	11-03-1998
			JP 4504731 T	20-08-1992
US 4123410	A	31-10-1978	NONE	

THIS PAGE BLANK (USPTO)